

SF-500

Property	Test Method	Value	Unit
Total Weight	-	680	g/SM
Tensile Strength (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	1700 1800	N/5cm
Elongation (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	20.0 26.0	%
Tearing Strength (warp/weft)	ISO 13937-2:2000 C.R.E. SINGLE TONGUE METHOD	130 170	N
Adhesion Strength (warp/weft)	ISO 2411:2000 C.R.E	135 121	N/5cm
Colorfastness to Weathering	ASTM G 155:2013	4	grade

For more information, visit our website at
www.star-flex.com