

**SF-1000**

Property	Test Method	Value	Unit
Total Weight	-	680	g/SM
Tensile Strength (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	2584 1779	N/5cm
Elongation (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	28.9 32.3	%
Tearing Strength (warp/weft)	ISO 13937-2:2000 C.R.E. SINGLE TONGUE METHOD	111 200	N
Adhesion Strength (warp/weft)	ISO 2411:2000 C.R.E	98 96	N/5cm
Colorfastness to Weathering	ASTM G 155:2013	4	grade

For more information, visit our website at  
[www.star-flex.com](http://www.star-flex.com)